

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
3 January 2002 (03.01.2002)

PCT

(10) International Publication Number
WO 02/01622 A2

- (51) International Patent Classification⁷: **H01L 21/316** (74) Agent: **MYERS BIGEL SIBLEY & SAJOVEC**; P.O. Box 37428, Raleigh, NC 27627 (US).
- (21) International Application Number: **PCT/US01/19787** (81) Designated State (*national*): **JP**.
- (22) International Filing Date: **21 June 2001 (21.06.2001)** (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data: **60/214,285** **26 June 2000 (26.06.2000)** **US**
- (71) Applicant: **NORTH CAROLINA STATE UNIVERSITY** [US/US]; Campus Box 7003, 1 Holladay Hall, Raleigh, NC 27695-7003 (US).
- (72) Inventors: **LUCOVSKY, Gerald**; 124 Lochwood West Drive, Cary, NC 27511-9744 (US). **PARSONS, Gregory**, N.; 2330 Hathaway Road, Raleigh, NC 27608 (US).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **NOVEL NON-CRYSTALLINE OXIDES FOR USE IN MICROELECTRONIC, OPTICAL, AND OTHER APPLICATIONS**

(57) Abstract: The invention relates to non-crystalline oxides of formulas (I) and (II), and methods of forming the same, along with field effect transistors, articles of manufacture, and microelectronic devices comprising the non-crystalline oxides.

WO 02/01622 A2

NOVEL NON-CRYSTALLINE OXIDES FOR USE IN MICROELECTRONIC, OPTICAL, AND OTHER APPLICATIONS

Cross-Reference to Related Applications

The present application claims priority to U.S. Provisional Application
5 No. 60/214,285 filed June 26, 2001, the disclosure of which is incorporated herein by reference in its entirety.

Field of the Invention

The invention generally relates to oxide-containing materials, along
10 with articles of manufacture comprising the same, and methods of forming the same.

Background of the Invention

As device dimensions are scaled according to the 1999 Technology
15 Roadmap for Semiconductors, 1999 Edition (<http://public.itrs.net>), the equivalent gate oxide thickness, EOT, should decrease below about 1.5nm. At this silicon dioxide (SiO₂) thickness, the direct tunneling current for a one volt potential drop across the oxide is typically greater than 1 A/cm⁻². Such a volt potential drop is potentially disadvantageous in that it begins to reduce the
20 ratio of on- to off-state current in a field effect transistor. In order to attempt to reduce the off-state leakage currents due to tunneling through SiO₂ and maintain a capacitance that is equivalent to that obtained with a SiO₂ dielectric with a physical thickness of 1.5 nm and below, alternative high-k dielectrics are being investigated. See e.g., J. Robertson, *J. Vac. Sci.*
25 *Technol. B* **18**(3) (2000) and G.D Wilk, et al., *J. Appl. Phys.* **89**, 5243 (2001). These high-k alternative dielectrics are potentially capable of providing the required levels of EOT for device scaling at larger physical thickness. Thus, a pathway for the potential reduction of tunneling current is provided. Other factors such as conduction band offset energies also are believed to play a

role in influencing tunnel leakage, and these offset energies generally decrease with increasing k .

Recently, aluminum oxide has been the focus of several studies. Klein *et al. Appl. Phys. Lett.* **75**, 4001 (1999) propose the deposition of aluminum oxide with a CVD growth method. This reference proposes a silicate layer being present at the interface on aluminum oxide and silicon, as measured by nuclear resonance profiling (NRP) and X-ray photoelectron spectroscopy (XPS). Gusev *et al. Appl. Phys. Lett.* **76**, 176 (2000) propose atomic layer CVD (ALCVD) where they investigated both the physical and electrical properties of an aluminum oxide layer. Gusey *et al.* propose that it is possible to deposit aluminum oxide on hydrogen-terminate silicon without forming an interfacial layer using NRP, medium energy ion scattering (MEIS), and high-resolution transmission electron microscopy (TEM).


Transistors with an equivalent gate oxide thickness of 0.96 nm with aluminum oxide as the material are proposed by Chin *et al. Tech. Dig. VLSI Symp*, 16 (2000). Chin *et al.* proposes that these devices have a D_{it} value greater than or equal to 3^{10} cm^{-2} and a positive flat band shift, indicating a negative fixed charge. Buchanan *et al., Tech. Dig. Intl. Electron Devices Meet*, 223 (2000) propose an nMOSFET formed by ALCVD Al_2O_3 with 0.08 μm gate lengths. This reference also proposes a negative fixed charge for devices with an equivalent oxide thickness of 1.3 nm.

Notwithstanding the above, there remains a need in the art for oxide materials that may be used in semiconductor devices which have the potential to reduce direct tunneling current in the devices.

Summary of the Invention

The present invention addresses the inadequacies of the prior art. In one aspect, the invention provides a non-crystalline oxide represented by the formula (I):

5



wherein:

A is an element selected from Group IIIA of the periodic table;

10 B is an element selected from Group VB of the periodic table;


O is oxygen;

M is an element selected from either Group IIIB or Group IVB of the periodic table; and

15 n ranges from about 0.5 to about 2.5, m ranges from about 1.5 to about 3.5, and x is a fraction ranging from 0 to 1.

In another aspect, the invention provides a non-crystalline oxide represented by the formula (II):

20



wherein:

Al is aluminum;

O is oxygen;

25 M is an element selected from either Group IIIB or Group IVB of the periodic table; and

j ranges from about 0.5 to about 4.5; k is equal to about 1; n ranges from about 0.5 to about 2.5, and m ranges from about 1.5 to about 3.5.

30 In another aspect, the invention provides methods of forming a non-crystalline oxide represented by the formulas (I) and (II) as described in greater detail hereinbelow.

In another aspect, the invention provides a field effect transistor. The field effect transistor comprises an integrated circuit substrate having a first surface, source and drain regions in the substrate at the first surface in a

spaced apart relationship, and a gate insulating layer on the substrate at the first surface between the spaced apart source and drain regions. The gate insulating layer comprises any of the non-crystalline oxides represented by formulas (I) or (II) described hereinbelow.

5 These and other aspects and advantages of the present invention are set forth hereinbelow.


Brief Description of the Drawings

10 **FIGS. 1a and 1b** illustrate layers used in microelectronic devices employing the non-crystalline oxides of the invention.

Detailed Description of the Preferred Embodiments

15 The invention will now be described in detail with reference to the following embodiments set forth herein. It should be appreciated that these embodiments merely serve to illustrate the invention and do not limit the scope of the invention. In the drawings, like numbers refer to like elements throughout. In addition, the term "on" is construed to mean a structure actually contacting an adjoining structure, or in close proximity to the adjoining structure without actually contacting it.

20 In one aspect, the invention provides a non-crystalline oxide represented by the formula (I):



25 wherein:

A is an element selected from Group IIIA of the periodic table;

B is an element selected from Group VB of the periodic table;

O is oxygen;


30 M is an element selected from either Group IIIB or Group IVB of the periodic table; and *n* ranges from about 0.5 to about 2.5, *m* ranges from about 1.5 to about 3.5, and *x* is a fraction ranging from 0 to 1.

In one embodiment encompassing the oxide represented by formula (I), A is aluminum (Al), B is tantalum (Ta), M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, and x is less than 0.25.

In another embodiment encompassing the oxide represented by formula (I), A is aluminum (Al), B is tantalum (Ta), M is selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, and x is less than 0.25.

In another aspect, the invention provides a non-crystalline oxide represented by the formula (II):

10



wherein:

Al is aluminum;

O is oxygen;

15 M is an element selected from either Group IIIB or Group IVB of the periodic table; and

j ranges from about 0.5 to about 4.5; k is equal to about 1; n ranges from about 0.5 to about 2.5, and m ranges from about 1.5 to about 3.5.

In one embodiment regarding the oxide represented by formula (II), M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, j is 4, and k is 1.

In another embodiment regarding the oxide represented by formula (II), M is selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, j is 3, and k is 1.


25 The novel materials of the invention are believed to have bonding properties, and hence electrical and optical properties, potentially similar to those of thin film silicates. In addition, this novel class of materials offers potential properties that may not be realized in conventional silicate alloys, and therefore opens new applications in microelectronics and other technologies.

30 This invention proposes novel non-crystalline oxides. In the non-crystalline oxides of formula (I), the SiO_2 component of the silicates is replaced by a Group IIIA-VA or B analog network structure such as AlPO_4 , or

AlTaO₄ as described in Serial No. 09/434, 607 filed November 5, 1999, the disclosure of which is incorporated herein by reference in its entirety ("the '607 application"). Although not intending to be bound by theory, alloying these binary alloys with additional metal oxides that are more ionic than Al₂O₃ is believed to introduce positive metal ions which interrupt or modify the AlO₂¹⁺ and (P or Ta)O₂¹⁺ network of the host oxide and provide bonding that is qualitatively similar to the SiO₂-based silicates. Other group three metal atoms with electronegativities greater than 1.6, e.g., Ga, may also be substituted for Al, and other group VA or B elements for Ta, e.g., As, Sb, and Nb and the like.

The non-crystalline oxides of formula (II) corresponds to stoichiometric or near stoichiometric aluminates, wherein the network component is believed to be significantly reduced by alloying with a more ionic metal oxide, such as Zr(Hf)O₂ or Y(La)₂O₃. Although not intending to be bound by theory, it is believed that the rationale for these structures derives from the vast number of aluminosilicate mineral species that exist in nature. The number of positive ions necessary for compensating the AlO₂¹⁺ groups may be determined by the number of these groups. For example, representative oxides in the second group include: Zr(Hf)(AlO₂)₄ and Y(La)(AlO₂)₃. These can also be described as mixed oxides as Zr(Hf)O₂(Al₂O₃)₂ and Y(La)₂O₃(Al₂O₃)₃. These materials can be customized to provide either neutral or charged bonding arrangements with elemental or compound semiconductors.

In addition to the above, the invention relates to methods of forming the non-crystalline oxides of the invention. More particularly, in one aspect, the invention provides a method of forming a non-crystalline oxide represented by the formula (I):



wherein A is an element selected from Group IIIA of the periodic table, B is an element selected from Group VB of the periodic table, O is oxygen, M is an element selected from either Group IIIB or Group IVB of the periodic table, n ranges from about 0.5 to about 2.5, m ranges from about 1.5 to about 3.5,

and x is a fraction ranging from 0 to 1. The method comprises delivering a gaseous source comprising element A, a gaseous source comprising element B, a gaseous source comprising element M, and a gaseous source comprising oxygen on a substrate such that the gaseous source comprising
5 element A, the gaseous source comprising element B, the gaseous source comprising element M, and the gaseous source comprising oxygen react to form the non-crystalline oxide represented by the formula (I).


Gaseous sources containing more than one element per source are encompassed by the invention (e.g., mixed sources). In a preferred
10 embodiment, the elements A, B and M are delivered in amounts necessary (i.e., sufficient) for achieving chemical 'stoichiometry, i.e., deposited thin films with the required ratios of network and network modifier ions to achieve stoichiometry of the their constituent oxides. Preferably, the gaseous sources comprising oxygen contain a sufficient amount of oxygen such that the
15 elements A, B and M are completely oxidized. In one embodiment, the delivery step is carried out as a deposition.

The oxygen which is present in the gaseous source of the above method of forming the non-crystalline oxide represented by formula (I) may be selected from a number of species. Exemplary species include, without
20 limitation, oxygen atoms, oxygen ions, oxygen metastables, oxygen molecular ions, oxygen molecular metastables, compound oxygen molecular ions, compound oxygen metastables, compound oxygen radicals, and mixtures thereof. In a preferred embodiment, the gaseous source comprising oxygen comprises O_2 or N_2O . It is particularly preferred that the formation of the non-
25 crystalline oxides take place in non-equilibrium chemical environments.

The depositing step of the method of forming the non-crystalline oxide represented by formula (I) may occur by various techniques. In one preferred embodiment, the depositing step includes a remote plasma-enhanced chemical vapor deposition occurring in a reactor, and wherein the remote-
30 plasma-enhanced chemical vapor deposition comprises subjecting the gaseous source comprising oxygen to radio-frequency plasma-excitation or microwave frequency plasma-excitation. The gaseous source comprising oxygen further comprises a rare gas element, and the gaseous oxygen-

containing source is injected into the reactor upstream relative to the gaseous source comprising element A, the gaseous source comprising element B, and the gaseous source comprising element M.

In another aspect, the invention provides a method of forming a non-crystalline oxide represented by the formula (II):



wherein:

Al is aluminum, O is oxygen, M is an element selected from either Group IIIB or Group IVB of the periodic table, j ranges from about 0.5 to about 4.5, k is equal to about 1, n ranges from about 0.5 to about 2.5, and m ranges from about 1.5 to about 3.5. The method comprises delivering a gaseous source comprising aluminum, a gaseous source comprising element M, and a gaseous source comprising oxygen on a substrate such that the gaseous source comprising aluminum, the gaseous source comprising element M, and the gaseous source comprising oxygen react to form the non-crystalline oxide represented by the formula (II).

In a preferred embodiment, the method of forming the non-crystalline oxide represented by formula (II) is preferably carried out in a manner such that elements aluminum and M are present in amounts sufficient to achieve chemical stoichiometry, with the term "chemical stoichiometry" being defined herein. Preferably, the gaseous source comprising oxygen contains a sufficient amount of oxygen such that the elements aluminum and M are completely oxidized.

In a preferred embodiment, the oxygen employed in the method of forming a non-crystalline oxide represented by the formula (II) may be selected from various species. Preferably, the oxygen in the gaseous source is selected from the group consisting of oxygen atoms, oxygen ions, oxygen metastables, oxygen molecular ions, oxygen molecular metastables, compound oxygen molecular ions, compound oxygen metastables, compound oxygen radicals, and mixtures thereof. In a preferred embodiment, the gaseous source comprising oxygen comprises O_2 or N_2O . Mixtures of the

above can also be employed. It is particularly preferred that the formation of the non-crystalline oxide represented by formula (II) take place in a non-equilibrium chemical environment.

The depositing step of the method of forming the non-crystalline oxide represented by formula (II) may be carried out according to various techniques. In one preferred embodiment, the depositing step is a remote plasma-enhanced chemical vapor deposition that occurs in a reactor. Preferably, the remote-plasma-enhanced chemical vapor deposition comprises subjecting the gaseous source comprising oxygen to radio-frequency plasma-excitation or microwave frequency plasma-excitation. The gaseous source comprising oxygen further comprises a rare gas element and the gaseous oxygen-containing source is injected into the reactor upstream relative to the gaseous source comprising aluminum and the gaseous source comprising element M.

Various gaseous sources comprising any of the applicable elements for the above methods may be employed for the purposes of the invention. Examples of gaseous sources comprising the elements may include, but are not limited to, alkoxide compounds, organometallic compounds, inorganic compounds, and mixtures thereof. Preferably, the alkoxide compound is selected from the group consisting of an ethoxide, a propoxide, and a butoxide. When the element is aluminum, it is preferred that the gaseous source comprises trimethyl aluminum. Other gaseous sources comprising the elements can be used such as organo-metallic source gases including those that are capable of producing the desired binary oxides (e.g., diketonates) along with other organo-metallics that contain metal-oxygen bonds. Other inorganic sources of the elements can be employed such as halides and nitrates. The gaseous sources comprising the element(s) can be derived through the evaporation of respective liquid sources comprising these elements, particularly in embodiments in which the deposition involves a physical deposition or a plasma chemical vapor deposition process.

The gaseous sources comprising the elements which are employed in the methods of the invention may further comprise other components such


as, for example, inert gases (e.g., argon (Ar) helium (He), or other noble gases, as well as mixtures thereof).

As alluded to hereinabove, a number of deposition techniques can be used in forming the non-crystalline oxides represented by formulas (I) and (II) of the invention. Examples of these techniques include, without limitation, those described in the '607 application. Exemplary techniques include, but are not limited to, a laser-assisted chemical vapor deposition, a direct or remote plasma assisted chemical vapor deposition, a electron cyclotron resonance chemical vapor deposition, and a reactive physical vapor deposition. In one embodiment, a remote plasma assisted chemical deposition is employed. Various reactive physical vapor depositions can be used such as, for example, a thermal evaporation, an electron beam evaporation, a parallel plate radio frequency (rf) sputtering, a direct current (dc) sputtering, a radio frequency (rf) magnetron sputtering, and a direct current (dc) magnetron sputtering. A reactive physical vapor deposition may also occur in the form of an atomic layer absorption process. The invention is often carried out by remote plasma-enhanced chemical vapor deposition (i.e., REPCVD).

The methods of the invention may be carried out under any number of temperature and pressure conditions. The methods of the invention may be carried out using known equipment, including, for example, a suitable reactor (e.g., reaction chamber or vessel). In one embodiment, alkoxide liquids comprising elements are injected into a reactor downstream from a remote radio-frequency excited plasma. Preferably, the alkoxides are liquids at room temperature, but at the temperature range employed in the reactor have sufficient levels of vapor to be transported into the reactor. A microwave plasma may be employed if so desired. In one embodiment, the processing pressure may range from about 200 to about 400 mTorr and the temperature of the substrate upon which the oxides are formed ranges from about 200°C to about 300°C. In a preferred embodiment, silane may be used as a precursor of Si and metal organics for Al and transition metals such as, for example, Ta, Zr, Hf, Y, and the like. An oxygen source encompassing those, without limitation, set forth herein, is preferably delivered upstream through

plasma, diluted with He. The silane and metal organics are preferably delivered downstream. In other various embodiments, nitrate sources can be employed for Ti, Hf, and Zr, e.g., $\text{Zr}(\text{NO}_3)_4$. Other techniques include, without limitation, atomic layer deposition using water as the oxidizing agent, and
5 silane metal organic sources for other constituents. An example of a source gas for Zr is Zr t-butoxide. Source gases for Ta and Al as well as other metals can also be used.

In another aspect, the invention relates to a field effect transistor. The field effect transistor comprises an integrated circuit substrate having a first
10 surface, source and drain regions in the substrate at the first surface in a spaced apart relationship, a gate insulating layer on the substrate at the first surface between the spaced apart source and drain regions. The gate insulating layer comprising a non-crystalline oxide represented by the formula (I):



wherein:


- A is an element selected from Group IIIA of the periodic table;
- B is an element selected from Group VB of the periodic table;
- 20 O is oxygen;
- M is an element selected from either Group IIIB or Group IVB of the periodic table;
- n ranges from about 0.5 to about 2.5;
- m ranges from about 1.5 to about 3.5; and
- 25 x is a fraction ranging from 0 to 1.

The non-crystalline oxide represented by the formula (I) employed in the field effect transistor may include, without limitation, all species described by this formula.

In one embodiment, the field effect transistor which employs the non-
30 crystalline oxide represented by formula (I) comprises a material selected from the group consisting of a Group III-V binary alloy, a Group III-V quaternary alloy, a Group III-nitride alloy, and combinations thereof.

In another embodiment, the substrate of the above field effect transistor comprises a Group III-V binary alloy selected from the group consisting of (Ga,Al)As, (In,Ga)As, and combinations thereof.

In another aspect, the invention also provides a field effect transistor which employs a non-crystalline oxide represented by the formula (II). The field effect transistor comprises an integrated circuit substrate having a first surface, source and drain regions in the substrate at the first surface in a spaced apart relationship, a gate insulating layer on said substrate at the first surface between said spaced apart source and drain regions, the gate insulating layer comprising a non-crystalline oxide represented by the formula (II):



wherein:

Al is aluminum, O is oxygen, M is an element selected from either Group IIIB or Group IVB of the periodic table, j ranges from about 0.5 to about 4.5, k is equal to about 1, n ranges from about 0.5 to about 2.5, and m ranges from about 1.5 to about 3.5.

In one embodiment, the substrate of the field effect transistor which employs a non-crystalline oxide of formula (II) comprises a material selected from the group consisting of a Group III-V binary alloy, a Group III-V quaternary alloy, a Group III-nitride alloy, and combinations thereof.

In another embodiment, the substrate of the field effect transistor which employs the non-crystalline oxide of formula (II) comprises a Group III-V binary alloy selected from the group consisting of (Ga,Al)As, (In,Ga)As, and combinations thereof.

Examples of proposed applications for the novel non-crystalline oxides of the invention include, without limitation, integration of the single layer or stacked non-crystalline oxides into gate stacks for NMOS, PMOS or CMOS applications involving Si, SiC and other compound semiconductors such as the III-V arsenides, antimonides, nitrides or phosphides, etc. In various embodiments, the layers can also be used in a number of articles of manufacture that comprise the non-crystalline oxides represented by the

formulas (I) and (II). Examples of articles of manufacture include, without limitation, passivation layers on other types of devices, e.g., photoconductors, photodiodes, light-emitting diodes, lasers, sensors, and micro-mechanical (MEMS) devices. Additionally, for example, they also can be used in devices
 5 with metal electrodes, such as spin-valves, or metal interface amplifiers. They also can be used for articles used sensor and catalysis applications.

The non-crystalline oxides of the invention may be used in a number of ways in various stacked structures that are employed in a variety of microelectronic devices such as, without limitation, those described herein.
 10 Examples of such structures include **100** and **200** as depicted in the drawings. For example, in one embodiment of a stacked structure depicted in **FIG. 1a**, interfacial layer **10** may comprise any number of appropriate materials such as, in one illustration, the oxides recited in the '607 application (e.g., AlTaO_4). Additionally, the interfacial layer **10** may comprise a non-
 15 crystalline oxide of formula (I) described herein or a non-crystalline oxide of formula (II) described herein. Any combinations of the above materials can be employed in interfacial layer **10**.

Referring again to **FIG. 1a**, present on the interfacial layer **10** is base layer **20**. The base layer **20** may comprise a non-crystalline oxide of the
 20 formula (I) described herein, a non-crystalline oxide of the formula (II) described herein, or any combination of these two materials, as well as any of the oxides disclosed in the '607 application. In another embodiment, the base layer **20** may comprise an oxide of the formula (III):



wherein D is Group IIIB or IVB oxide and z is an integer, preferably 3 or 4. In preferred embodiments, the oxide of formula may be selected from $\text{Hf}(\text{AlO}_2)_4$ or $\text{Y}(\text{AlO}_2)_3$, as well as combinations thereof. Combinations of any
 30 of the above disclosed oxides can be utilized in the base layer **20**, as well as others.

In addition, as shown in **FIG. 1b**, a surface/interface layer **30** can be

employed on top of base layer 20. In one embodiment, layer 30 may comprise nitrogen. In other embodiments, layer 30 may comprise any number of oxides such as, without limitation, an oxide of the second group (i.e., Group (II)) described herein (e.g., $\text{Zr(Hf)(AlO}_2)_4$ or $\text{Y(La)(AlO}_2)_3$), an
5 oxide disclosed in the '607 application (e.g., TiAlO_4) as well as others, alone or in combination with nitrogen. In various embodiments, metal is on top of surface/interface layer 30. Accordingly, elements employed in various oxides may be selected to match the contacting metal. Combinations of any of the above materials can be employed in layer 30.

10 One novel and unusual feature is a recognition that macroscopically neutral covalent random network structures comprised of alternative charged network groups can have properties tailored by the addition of other metal ions, as in conventional silicates with a neutral SiO_2 network forming group. A second novel and unusual feature is the identification of networks that have
15 constituents which can provide neutral or charged network bonding at interfaces according to their composition. The disclosure of these materials allows for new potential options for integration into devices, most noteworthy is the ability to control the nature of the band bending at elemental and compound semiconductor interfaces. Surface modification also allows for
20 unique opportunities for sensors and/or catalytic applications. As such, the novel materials of the invention can be integrated into devices with elemental or compound semiconductors as gate dielectric or passivation layers for microelectronic or optical applications. They can also be used metals in spin valve devices and metal interface amplifiers. Finally, they provide pathways
25 to surface modification for applications in sensing and catalysis.


The invention has been described in detail with respect to the embodiments set forth hereinabove. It should be appreciated that the embodiments are merely set forth to illustrate the invention, and do not serve to limit the invention as defined by the claims.

30 The invention has been described with respect to various embodiments set forth in the specification and drawings. It should be appreciated that these embodiments are for illustrative purposes only, and do not limit the scope of the invention as described by the claims that follow.

THAT WHICH IS CLAIMED:

1. A non-crystalline oxide represented by the formula (I):

5



wherein:

A is an element selected from Group IIIA of the periodic table;

B is an element selected from Group VB of the periodic table;

10

O is oxygen;

M is an element selected from either Group IIIB or Group IVB of the periodic table; and

n ranges from about 0.5 to about 2.5, m ranges from about 1.5 to about 3.5, and x is a fraction ranging from 0 to 1.

15


2. The oxide according to Claim 1, wherein A is aluminum (Al), B is tantalum (Ta), M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, and x is less than 0.25.

20

3. The oxide according to Claim 1, wherein A is aluminum (Al), B is tantalum (Ta), M is selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, and x is less than 0.25.

25

4. A method of forming a non-crystalline oxide represented by the formula (I):



- 30 wherein A is an element selected from Group IIIA of the periodic table, B is an element selected from Group VB of the periodic table, O is oxygen, M is an element selected from either Group IIIB or Group IVB of the periodic table, n

ranges from about 0.5 to about 2.5, m ranges from about 1.5 to about 3.5, and x is a fraction ranging from 0 to 1, said method comprising:

delivering a gaseous source comprising element A, a gaseous source comprising element B, a gaseous source comprising element M, and a

- 5 gaseous source comprising oxygen on a substrate such that the gaseous source comprising element A, the gaseous source comprising element B, the gaseous source comprising element M, and the gaseous source comprising oxygen react to form the non-crystalline oxide.

10

5. The method according to Claim 4, wherein elements A, B, and M are present in amounts sufficient to achieve chemical stoichiometry, and wherein the gaseous source comprising oxygen contains a sufficient amount of oxygen such that the elements A, B, and M are completely oxidized.

15

6. The method according to Claim 4, wherein the oxygen in the gaseous source comprising oxygen-containing source is selected from the group consisting of oxygen atoms, oxygen ions, oxygen metastables, oxygen molecular ions, oxygen molecular metastables, compound oxygen molecular
20 ions, compound oxygen metastables, compound oxygen radicals, and mixtures thereof.

25

7. The method according to Claim 4, wherein the gaseous source comprising oxygen comprises O₂ or N₂O.

8. The method according to Claim 4, wherein said depositing step is a remote plasma-enhanced chemical vapor deposition occurring in a reactor, and wherein the remote-plasma-enhanced chemical vapor deposition comprises:

30 subjecting the gaseous source comprising oxygen to radio-frequency plasma-excitation or microwave frequency plasma-excitation, the gaseous source comprising oxygen further comprising a rare gas element;

wherein the gaseous oxygen-containing source is injected into the reactor upstream relative to the gaseous source comprising element A, the gaseous source comprising element B, and the gaseous source comprising element M.

5

9. The method according to Claim 4, wherein A is aluminum (Al), B is tantalum (Ta), M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, and x is less than 0.25.


10

10. The method according to Claim 4, wherein A is aluminum (Al), B is tantalum (Ta), M is selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, and x is less than 0.25.

15

11. A field effect transistor comprising:
an integrated circuit substrate having a first surface;
source and drain regions in said substrate at said first surface in a spaced apart relationship; and
a gate insulating layer on said substrate at said first surface between said spaced apart source and drain regions, said gate insulating layer comprising a non-crystalline oxide represented by the formula (I):

20



wherein:

25

A is an element selected from Group IIIA of the periodic table;

B is an element selected from Group VB of the periodic table;

O is oxygen;

M is an element selected from either Group IIIB or Group IVB of the periodic table;

30

n ranges from about 0.5 to about 2.5;

m ranges from about 1.5 to about 3.5; and

x is a fraction ranging from 0 to 1.

12. The field effect transistor according to Claim 11, wherein the substrate comprises a material selected from the group consisting of a Group III-V binary alloy, a Group III-V quaternary alloy, a Group III-nitride alloy, and combinations thereof.

5

13. The field effect transistor according to Claim 11, wherein the substrate comprises a Group III-V binary alloy selected from the group consisting of (Ga,Al)As, (In,Ga)As, and combinations thereof.

10

14. The field effect transistor according to Claim 11, wherein A is aluminum (Al), B is tantalum (Ta), M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, and x is less than 0.25.

15

15. The field effect transistor according to Claim 11, wherein A is aluminum (Al), B is tantalum (Ta), M is selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, and x is less than 0.25.

20

16. A microelectronic device comprising a non-crystalline oxide according to Claim 1.

17. The microelectronic device according to Claim 16, wherein said microelectronic device comprises a base layer and an interfacial layer positioned thereon.

25

18. The microelectronic device according to Claim 17, wherein the non-crystalline oxide represented by formula (I) is present in said interfacial layer.

30

19. The microelectronic device according to Claim 17, wherein the non-crystalline oxide represented by formula (I) is present in the base layer.

20. The microelectronic device according to Claim 17, wherein the base layer comprises an oxide of the formula (III):



wherein D is Group IIIB or IVB oxide and z is 3 or 4.


21. The microelectronic device according to Claim 20, wherein the
10 oxide of the formula (III) is selected from the group consisting of $\text{Hf}(\text{AlO}_2)_4$, $\text{Y}(\text{AlO}_2)_3$, and combinations thereof.

22. An article of manufacture comprising the non-crystalline oxide represented by formula (I) according to Claim 1.

15

23. The article of manufacture according to Claim 22, wherein the article of manufacture is selected from the group consisting of photoconductors, photodiodes, light-emitting diodes, lasers, sensors, micro-mechanical (MEMS) devices, and devices with metal electrodes, articles used
20 in sensor applications, and articles used in catalysis applications.

24. A non-crystalline oxide represented by the formula (II):



wherein:

Al is aluminum;

O is oxygen;

M is an element selected from either Group IIIB or Group IVB of the
30 periodic table; and

j ranges from about 0.5 to about 4.5; k is equal to about 1; n ranges from about 0.5 to about 2.5, and m ranges from about 1.5 to about 3.5.

25. The oxide according to Claim 24, wherein M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, j is 4, and k is 1.

5 26. The oxide according to Claim 24, wherein M is selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, j is 3, and k is 1.

27. A method of forming a non-crystalline oxide represented by the formula (II):



wherein:

Al is aluminum, O is oxygen, M is an element selected from either Group IIIB or Group IVB of the periodic table, j ranges from about 0.5 to about 4.5, k is equal to about 1, n ranges from about 0.5 to about 2.5, and m ranges from about 1.5 to about 3.5, said method comprising:

delivering a gaseous source comprising aluminum, a gaseous source comprising element M, and a gaseous source comprising oxygen on a substrate such that the gaseous source comprising aluminum, the gaseous source comprising element M, and the gaseous source comprising oxygen react to form the non-crystalline oxide.

28. The method according to Claim 27, wherein elements aluminum and M are present in amounts sufficient to achieve chemical stoichiometry, and wherein the gaseous source comprising oxygen contains a sufficient amount of oxygen such that the elements aluminum and M are completely oxidized.

29. A method according to Claim 27, wherein the oxygen in the gaseous source comprising oxygen-containing source is selected from the group consisting of oxygen atoms, oxygen ions, oxygen metastables, oxygen molecular ions, oxygen molecular metastables, compound oxygen molecular

ions, compound oxygen metastables, compound oxygen radicals, and mixtures thereof.

30. The method according to Claim 27, wherein the gaseous source
5 comprising oxygen comprises O₂ or N₂O.

31. The method according to Claim 27, wherein said depositing step is a remote plasma-enhanced chemical vapor deposition occurring in a reactor, and wherein the remote-plasma-enhanced chemical vapor deposition
10 comprises:


subjecting the gaseous source comprising oxygen to radio-frequency plasma-excitation or microwave frequency plasma-excitation, the gaseous source comprising oxygen further comprising a rare gas element;

wherein the gaseous oxygen-containing source is injected into the
15 reactor upstream relative to the gaseous source comprising aluminum and the gaseous source comprising element M.

32. The method according to Claim 27, wherein M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, j is 4, and k is 1.
20

33. The method according to Claim 27, wherein M is selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, j is 3, and k is 1.

34. A field effect transistor comprising:
25 an integrated circuit substrate having a first surface;
source and drain regions in said substrate at said first surface in a spaced apart relationship; and
a gate insulating layer on said substrate at said first surface between said spaced apart source and drain regions, said gate insulating layer
30 comprising a non-crystalline oxide represented by the formula (II):



wherein:

Al is aluminum, O is oxygen, M is an element selected from either Group IIIB or Group IVB of the periodic table, j ranges from about 0.5 to about 4.5, k is equal to about 1, n ranges from about 0.5 to about 2.5, and m ranges
5 from about 1.5 to about 3.5.

35. A field effect transistor according to Claim 34, wherein the substrate comprises a material selected from the group consisting of a Group III-V binary alloy, a Group III-V quaternary alloy, a Group III-nitride alloy, and
10 combinations thereof.

36. A field effect transistor according to Claim 34, wherein the substrate comprises a Group III-V binary alloy selected from the group consisting of (Ga,Al)As, (In,Ga)As, and combinations thereof.
15

37. The field effect transistor according to Claim 34, wherein M is selected from hafnium (Hf) or zirconium (Zr), n is 1, m is 2, j is 4, and k is 1.

38. The field effect transistor according to Claim 34, wherein M is
20 selected from yttrium (Y) or lanthanum (La), n is 2, m is 3, j is 3, and k is 1.

39. A microelectronic device comprising a non-crystalline oxide according to Claim 24.

25 40. The microelectronic device according to Claim 39, wherein said microelectronic device comprises a base layer and an interfacial layer positioned thereon.

41. The microelectronic device according to Claim 39, wherein the
30 non-crystalline oxide represented by formula (II) is present in said interfacial layer.

42. The microelectronic device according to Claim 39, wherein the non-crystalline oxide represented by formula (II) is present in the base layer.

43. The microelectronic device according to Claim 39, wherein the base layer comprises an oxide of the formula (III):



wherein D is Group IIIB or IVB oxide and z is 3 or 4.

44. The microelectronic device according to Claim 43, wherein the
10 oxide of the formula (III) is selected from the group consisting of $\text{Hf}(\text{AlO}_2)_4$, $\text{Y}(\text{AlO}_2)_3$, and combinations thereof.

45. An article of manufacture comprising the non-crystalline oxide represented by formula (II) according to Claim 24.
15

46. The article of manufacture according to Claim 45, wherein the article of manufacture is selected from the group consisting of photoconductors, photodiodes, light-emitting diodes, lasers, sensors, micro-mechanical (MEMS) devices, and devices with metal electrodes, articles used
20 in sensor applications, and articles used in catalysis applications.